

COPPER ALLOY POWDER

BRONZE (PRE-ALLOYED)-IRREGULAR

Product: BN 8515 IS

Characteristics	UOM	Test Method	Specification
<u>Sieve analysis:</u> +75 μm -75+45 μm - 45 μm	% % %	ASTM B-214	3 max Balance 80 min
<u>Chemical analysis:</u> Copper Tin Zinc	% % %	AAS	83 – 85 14 – 16 1.5 – 2.5

BN 8515 IS Alloying of > 99.99 % high pure copper and tin ingots followed by air atomization, irregular shaped powder, used for the applications like Abrasives, Adhesives, Automobile parts, Bearings, Brake Linings, Chemicals, Diamond tools, Oil filters, Plastics, Powder Metallurgy parts, Sintering parts, Watch components etc.

The data on this technical information sheet correspond with the current status of our knowledge and experience. The liability for the application and processing of our products lies with the buyer, and he is also responsible for observing any third party rights. We reserve the right to alter any product data as a result of technical progress or further developments in the manufacturing process.

MEPCO

Thirumangalam,
Madurai
PIN: 625706
Tamilnadu, India
Phone: + 91 4549 280599
Fax: +91 4549 281273

E-mail: info@mepco.co.in
Web: www.mepco.co.in

Edition: 09.03.2019
Page 1 of 1