

SPHERICAL ALUMINIUM POWDER

Product: D50S15

Characteristics	UOM	Test Method	Specification
Average Particle size (Fisher Number) (FSSS)	µm	ASTM B-330	13.0 – 17.0
D50	µm	Malvern-2000	13.5 – 16.5
<u>Chemical analysis:</u> Iron Silicon Other metallic impurities (Cu+Mn+Mg+Zn) Aluminium (by dif)*	% % % %	AAS	0.35 max 0.15 max 0.05 max 99.5 min
Active Aluminium content	%	IS-438	98.5 min

*(exclusive of total metallic impurities and inclusive of oxides of aluminium)

Made out of primary high pure Aluminium ingot of > 99.7 % purity, by gas atomization, spherical in shape.

The data on this technical information sheet correspond with the current status of our knowledge and experience. The liability for the application and processing of our products lies with the buyer, and he is also responsible for observing any third party rights. We reserve the right to alter any product data as a result of technical progress or further developments in the manufacturing process.

MEPCO