

Technical Data Sheet

ALUMINIUM POWDER (FLAKE)

Trade Mark: PO55

Characteristics	UOM	*Test Method	Specification
<u>Sieve analysis:</u>			
Residue on Sieve 250 µm	%	M/QA/SOP/003	2 max
Passing through sieve 45 µm	%	M/QA/SOP/003	30 - 45
Apparent Density	g/cc	M/QA/SOP/004	0.145 – 0.210
Burning Property	sec	M/QA/SOP/009	Nil
Matter Soluble in organic solvent	%	M/QA/SOP/006	1.0 max
Active Aluminium content	%	M/QA/SOP/016	94 min
Acid Insoluble (Gritty matter)	%	M/QA/SOP/044	Nil

* M/QA/SOP/003, M/QA/SOP/004, M/QA/SOP/009, M/QA/SOP/006, M/QA/SOP/016 & M/QA/SOP/044 are based on ISO-1247, ASTM B-417, In-house, ISO-1247, IS: 438 & DRDO procedure respectively.

PO-55 Pyrotechnic lamellar Aluminium Powder made out of primary high pure Aluminium ingot of > 99.7 % purity, by atomization of molten Aluminium liquid, followed by safe dry ball milling process, used for making Aluminium Phosphide pesticide and also for construction chemical applications.

The data on this technical information sheet correspond with the current status of our knowledge and experience. The liability for the application and processing of our products lies with the buyer, and he is also responsible for observing any third party rights. We reserve the right to alter any product data as a result of technical progress or further developments in the manufacturing process.

MEPCO

Thirumangalam,
Madurai
PIN: 625706
Tamilnadu, India
Phone: + 91 4549 280599
Fax: +91 4549 281273

E-mail: info@mepco.co.in
Web: www.mepco.co.in

Edition: 02.01.2023
Page 1 of 1